

N58479/T508 Polyester Filler

Product Description

N58479/T508 is a two component polyester based filler for direct application to metal and composite substrates, for filling of holes and surface imperfections.

- High viscosity
- Excellent sandability
- Ambient curing
- Long pot life enables filling of large areas using a single mix

Components



Mix Ratio (by weight)

- | | |
|-------------------------|-----------|
| • N58479 (Base) | 100 parts |
| • N59029NV-3 (Hardener) | 1.5 part |

Specifications



N58479/T508 is qualified to the following specification:

- ECS 2202

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

N58479/T508 meets the requirements of following specification:

- DAN 1090

Surface Preparation and Pretreatment



Ensure surface is clean, dry and intact, using a high performance cleaner, DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended. Maximum adhesion is achieved on well abraded surfaces such as metal, wood and glass fibre reinforced polyester.

N58479/T508

N58479/T508 Polyester Filler

Instructions for Use



Before adding the hardener to the base, thoroughly stir or shake the base component until a smooth uniform mix is obtained. Immediately after adding the hardener to the base, stir thoroughly until uniform.

Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.




Induction Time:

Not applicable



Viscosity: (23°C/73°F)

Not applicable - Product supplied in the form of a paste



Pot Life:

28-35 minutes @ room temperature of 18-20°C (64-68°F)

Application Guidelines

Recommended Application Conditions:

Temperature	15-35°C (59-95°F)
Relative Humidity	30-85%

Application:

Apply as required using a filler knife or spatula




Theoretical Coverage: (ready for use)

8 m²/Lt @ 100µm dry film thickness
320 ft²/US gal @ 4 mil dry film thickness

Recommended Dry Film Thickness:

Up to 100µm
4 mil



Dry Film Density:

1.8g/cm³
15lbs/US gal

N58479/T508 Polyester Filler

Dry Film Weight:

210 g/m² @ 100 µm dry film thickness

8400 lbs/ft² @ 4 mil dry film thickness

Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.

Equipment:



Applicable using a filler knife or plastic/rubber spatula

Physical Properties



Colour:

White




Gloss:

Not applicable



Drying Times	23°C (73°F)
Dry to Sand	1.5 to 2 hours
Dry to Overcoat	2 to 3 hours

Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.



Flash Off Time:

Not applicable



VOC: (ASTM)

Mixed ready for use

<250 g/Lt



Flash Point:

N58479 Base Component

31°C (88°F)

N59029NV-3 Hardener

Not Applicable

N58479/T508 Polyester Filler

Shelf Life:

N58479

9 months in original unopened container

N59029NV-3 Hardener

9 months in original unopened container

Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.

N58479/T508 Polyester Filler

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC – South Europe

Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Desoclean, Desothane, Desoprime and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace
Sealants and Coatings
Darlington Road
Shildon, Co Durham UK
DL4 2QP
www.ppgaerospace.com
Issue Date: 07/22
Lit: 4314