# ANDEROL PRODUCT DATA SHEET

# **ROYCO<sup>®</sup> 482** CORROSION PREVENTATIVE COMPOUND FOR RECIPROCATING AIRCRAFT ENGINES

#### **GENERAL INFORMATION**

ROYCO 482 is a light green rust and corrosion preventative oil commonly used to preserve aircraft internal combustion engines. The ashless anti corrosion additive package and highly refined petroleum base oils protect the engine by minimizing the effects of humidity and neutralizing the acidic components of engine oil oxidation and combustion by-products. ROYCO 482 is designated a preservative under MIL-STD-2073-1C.

### **TYPICAL PROPERTIES:**

PROPERTIES	ROYCO 482
API Gravity, 60/60 °F	26.7
Kinematic Viscosity, cSt	
@ 100 °F	265.0
@ 210 °F	20.0
Aircraft Oil Grade	1100
SAE Viscosity	50
Pour Point, °F	5
Flash Point, °F	565
Carbon Residue, % wt.	0.45
Ash, % wt. ASTM D-482	0.0100
HBr Neutralization Test	PASS
Lead Corrosion, 300°F/4 hrs., mg/in2	14.3
Copper Corrosion, ASTM D-130	1B slight tarnish
Rust Protection, Humidity Cabinet	PASS

<sup>®</sup>ANDEROL is a reg. trademark of ANDEROL Inc.

This information is furnished without warranty, representation, inducement, or license of any kind, except that it is accurate to the best of OUR knowledge or obtained from sources believed by ANDEROL to be accurate. ANDEROL does not assume any legal responsibility for use of reliance upon it. Only chemists or chemically qualified lab technicians should carry out tests. Before using any chemical, read its label and Material Safety Data Sheet.

For more information please refer to the relevant Material Safety Data Sheet accompanying each product.

## APPLICATIONS

ROYCO 482 is normally used as a preservation grade engine oil for the internal preservation of engines or engine parts and accessories during moderate outdoor to long term indoor storage periods. This oil can also be used as a "flyaway" oil for reciprocating engines however operation of engines preserved with the diluted material should be limited to a maximum of fifty hours before oil change

The engine to be preserved should be filled to normal capacity with ROYCO 482 and then run at idle until the engine reaches normal operating temperature (approx. 10 - 15 minutes.) Upon shutdown the internal surfaces of the engine are now protected from rust and corrosion.

### **ADVANTAGES**

- Excellent thermal and oxidative stability
- Offers outstanding rust and corrosion protection

#### COMPATABILITY

Turbine engines using synthetic engine lubricating oils should use a Mil-C-8188 corrosion preventative concentrate. Turbine engines using lubricants compatible with mineral based fluids should use ROYCO 483 corrosion preventative.

R482: 11/30/01: edited 10/15/04 by GMG



ANDEROL Inc. PO Box 518, 215 Merry Lane East Hanover, New Jersey USA Tel: 888-ANDEROL Or Tel: (973) 887-7410 Fax: (973) 884-3825 E-mail: info@anderol.com