


Flame Retardant Fiberglass Tape



Backing:	Fiberglass Cloth
Adhesive:	Rubber
Liner:	LDPE Film
Colors:	White (Unprinted)
Specifications:	
FAA	FAR 25,853(a), FAR 25.855(d)
Boeing	737-SL-25-115-B, 757-SL-25-085-B, 747-SL-25-195-B, 767-SL-25-112-B, 777-SL-25-037-B
Bombardier	DSC 91-18-2A
Standard Sizes:	2in x 36yd, 3in x 36yd

Applications

- Seaming and repairing cargo compartment liners on freight carrying aircraft
- Covering pins and rivets
- Challenging applications where high adhesion and flame resistance is critical
- Metal surface protection during soldering or welding

Features

- Fiberglass Cloth
- Rubber Adhesive

Benefits

- Super high tensile strength
- Resists flame penetration for added safety
- Lightweight construction - saves money
- Conformable to handle curves and corners
- Maintains seal under heavy loads
- Resists flagging and lifting
- Deca-BDE Free

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness	8.0 mils	0.203 mm	ASTM D-1000
Adhesion to Steel	50 oz/in	5.47 N/cm	PSTC-101
Tensile Strength	150 lb/in	262.69 N/cm	ASTM D-1000
Weight	8.1 oz/yd ²	274.7 g/m ²	ASTM D-1000
Operating Temperature	-10 to 200 °F	-23 to 93 °C	ASTM D-1000
Exiting Time	0 sec		FAR 25.853(a)/25.855(d)
Burn Length	0.25"	Drip Exiting N/A	FAR 25.853(a)
Flame Penetration	N/A	After Glow 0 sec	FAR 25.855(d)

Recommended Storage Conditions: 60-80 °F at 40-60% RH
 Standard Shelf Life (at 25 °C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.