



Product description:

CORROSION INHIBITING COMPOUND

FEATURES:

- A long lasting, water displacing, corrosion inhibiting compound
- Cor-Ban® 22 formula is based on the Cor-Ban® 27L CIC
- A soft and self healing finished coating

KEY BENEFITS:

- No cracking or flaking to -60°F (-51°C)
- Cor-Ban® 22 can be applied to corroded areas to prevent further corrosion from occurring
- Provides additional barrier protection for corrosion prone internal steel bores of horizontal pivot shafts and landing gear bogies
- ► Film is detectable and non-sagging
- Solvent removable
- ► A military approved CIC for stopping corrosion on pre-corroded metal parts
- Highly penetrating formula delivers the corrosion protection of Cor-Ban® 27L into faying surfaces

Rev: 20062E 11-24-2021











Product description:

CORROSION INHIBITING COMPOUND

KEY BENEFITS:

- Preferred CIC for routine maintenance
- > 4000 hours of salt spray

SPECS:

- Boeing BMS 3-23 (Meets requirements)
- NSN 8030-01-523-4290 (16 fl oz (473 ml) Aerosol)
- NSN 8030-01-531-7352 (5 Gallon (18.9L) Pail)
- T.O. 1C-130A-23 (Called out)
- T.O. 1C-5A-23 (Called out)

APPLICATIONS:

- ✓ Apply by conventional airless, air-operated spray equipment, or by aerosol
- ✓ Cor-Ban® 22 can be applied over pre-existing corrosion
- ✓ The coating can be applied as thin as 1 mil (25 microns) film thickness to achieve the desired corrosion protection
- ✓ The Cor-Ban® 22 aerosol can be used in conjunction with the Formit® extensions to provide targeted spray to areas that may be difficult to reach but need to be coated. Please refer to the Formit® technical data sheet for more information.
- ✓ All properties represented were achieved with a wet film thickness of 1.0 mils (25 microns). This wet film thickness can be measured with **Zip-Chem®** 's **Wet Film Thickness Gauge**.
- ✓ One aerosol can covers approximately 90 ft² (8.3 m²)
- ✓ Paste application of Cor-Ban® 22 is available as Cor-Ban® 27L







Product description:

CORROSION INHIBITING COMPOUND

PHYSICAL PROPERTIES:

Color: reddish-brown

Compatibility Cd, Mg, AI: Pass

Corrosion Resistance ASTM B-117: >4000 hours on Steel

► Flash Point: 105°F (40°C)

► Fungal Growth per Fed-STD-810 Method 508.7: 0 (No Microbial Growth)

Low Temp Flaking: Pass

Material VOC: 538 g/L (4.4 Lbs/Gal)

Non-Volatiles: 33%

► Penetration: BMS 3-23F pass

Solvent Type: Aliphatic

► Specific Gravity: 0.82

► Water Displacement: 0% Rust

Water Resistance: Pass







Product description:

CORROSION INHIBITING COMPOUND

AVAILABLE PACK SIZES:

- Case of 12 of 16 fl oz (473 ml) Aerosols-007047
- Case of 24 of 4 fl oz (118 ml) Aerosols-103734
- Case of 4 each Gallon (4 each of 3.8L) Cans-009400
- ► 5 Gallon (18.9L) Pail-007049
- ▶ 55 Gallon (208L) Drum-007050
- Special Packaging Upon Request

